```
L6
     ANSWER 19 OF 24 CA COPYRIGHT 2006 ACS on STN
ΑN
     122:87744 CA
     Entered STN: 18 Feb 1995
ED
TI
     Admixtures for cement, and cement compositions
     containing the admixtures
     Kyogoku, Yasuhiro; Kanamori, Shinji; Ida, Makio; Mihara, Toshio
IN
     Denki Kagaku Kogyo Kk, Japan
PΑ
so
     Jpn. Kokai Tokkyo Koho, 5 pp.
     CODEN: JKXXAF
DT
     Patent
LA
     Japanese
     ICM C04B022-12
IC
     ICS C04B022-14; C04B024-26; C04B028-02; C04B028-22
CC
     58-1 (Cement, Concrete, and Related Building Materials)
FAN.CNT 1
     PATENT NO.
                        KIND
                                DATE
                                            APPLICATION NO.
                                                                   DATE
     -----
                         ----
                                -----
     JP 06256053
                                19940913
                                                                   19930301
                         A2
                                            JP 1993-39922
                                19930301
PRAI JP 1993-39922
CLASS
PATENT NO.
                        PATENT FAMILY CLASSIFICATION CODES
                CLASS
JP 06256053
                ICM
                        C04B022-12
                ICS
                        C04B022-14; C04B024-26; C04B028-02; C04B028-22
                IPCI
                       C04B0022-12 [ICM,5]; C04B0022-14 [ICS,5]; C04B0024-26
                        [ICS,5]; C04B0028-02 [ICS,5]; C04B0028-22 [ICS,5]
AB
    Th admixts. contain latent hydraulic binders, Ca fluoroaluminates, inorg.
     sulfates, thickeners, and water reducing agents, and
    are mixed with cement to give the cement compns.
    Concrete prepared from a composition containing portland cement 56,
     fly ash 24, Ca fluoroaluminate 10, and II-type anhydrite
    10 weight parts 460, water 158.1, fine aggregate 889, coarse
    aggregate 741, and Darex Super 100PHX (water reducing
     agent) 6.9 kg/m3, with addition of Me cellulose 20, and air-entraining agent
    23 g/m3, had excellent workability and 3-, 7-, and 28-day compressive
    strength 260, 340, and 480 kg/cm2, resp.
ST
    calcium fluoroaluminate sulfate cement; fly
    ash calcium fluoroaluminate concrete
IT
    Concrete
```

- Cement - flyash - water - water reducing again